



## Product Overview

*We create your resources*

	Product		Density ISO 1183	MFR ISO 1132
Pellet <sup>1</sup>	HD	GR H70	0,94 - 0,96 g/cm <sup>3</sup>	190°C/5kg 0,7 – 1,0 g/10 min
	HD	GR H80	0,95 g/cm <sup>3</sup>	190°C/2,16kg 0,5 – 0,95 g/10 min
	HD	GR H90	0,98 g/cm <sup>3</sup>	190°C/2,16kg 0,5 – 0,9 g/10 min
	LD	GR L30	0,92 - 0,94 g/cm <sup>3</sup>	190°C/2,16kg 0,7 – 1,2 g/10 min

Regrind	HD	MG HD 99	0,94 - 0,96 g/cm <sup>3</sup>	190°C/2,16kg 1,5 – 3,0 g/10 min
	HD + LD <sup>2</sup>	MAG HD 99	0,94 - 0,96 g/cm <sup>3</sup>	190°C/2,16kg 1,5 – 3,0 g/10 min

Agglomerate	LD	AG LD 99	0,94 - 0,96 g/cm <sup>3</sup>	190°C/2,16kg 0,7 – 1,2 g/10 min
	PO	AG PO 99	0,91 - 0,96 g/cm <sup>3</sup>	190°C/2,16kg 0,6 – 1,5 g/10 min

<sup>1</sup> All Pellets can be delivered light grey and black coloured

<sup>2</sup> HD Regrind mixed with LD Agglomerate

Packed in Big Bag on pallet. A hand over by silo transportation is possible.

The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no guarantee is made as to the suitability, accuracy, reliability and completeness of such information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use.